

Standard Process for Rapid Thermal Annealing

Si :	1050°C	10sec
	750 °C	30sec
	450 °C	30sec
Ge :	550°C	10sec
	450 °C	30sec
	350 °C	30sec

The Ge process chamber is scheduled for use only on Wednesdays.